

Item No. 232S
Rolling (Pneumatic Tire)

232S.1 Description

This item shall govern compaction of embankment, flexible base, surface treatments or pavements by the operation of approved pneumatic tire rollers as herein specified and as directed by the Engineer or designated representative.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

232S.2 Submittals

The submittal requirements of this specification item may include:

- A. A plan describing the condition of each roller proposed for the work, as well as the type of traction (self propelled or drawn), Type, size, weight, tire pressure and configuration for each individual roller, and
- B. The operating speed proposed for each individual roller.

232S.3 Equipment

A. General Requirements

When used on seal coats, asphaltic surface treatments and bituminous mixture pavements, the roller shall be self propelled and equipped with smooth tread tires whether "Rolling (Light Pneumatic Tire)" or "Rolling (Medium Pneumatic Tire)" is specified on the Drawings. The roller shall be so constructed as to be capable of being operated in both a forward and a reverse direction. When used on bituminous mixture pavements, the roller shall have suitable provisions for moistening the surface of the tires while operating.

When turning is impractical or detrimental to the work and when specifically directed by the Engineer or designated representative, the roller shall be capable of being operated in a forward or backward motion.

In lieu of the rolling equipment specified, the Contractor may, upon written permission of the Engineer or designated representative, operate other compacting equipment that will produce equivalent relative compaction in the same period of time as the specified equipment. If the substituted compaction equipment fails to produce the desired compaction within the same period of time as would be expected of the specified equipment, as determined by the Engineer or designated representative, its use shall be discontinued and the Contractor will be required to furnish the specified equipment.

Rollers shall be maintained in good repair and operating condition and shall be approved by the Engineer or designated representative.

Tire pressure is critical to successful operation of the roller. The Contractor shall have equipment on the construction site to inflate tires as required.

B. Light Pneumatic Tire Roller

The light pneumatic tire roller shall consist of not less than 9 pneumatic tired wheels, running on axles in such manner that the rear group of tires will cover the entire gap between adjacent tires of the forward group and mounted in a rigid frame and provided with a loading platform or body suitable for ballast loading. The front axle shall be attached to the frame in such a manner that the roller may be turned within a minimum circle. The pneumatic tire roller, under working conditions, shall have an effective rolling width of approximately 60 inches (1.5 meters) and shall be so designed that by ballast loading, the total load may be varied uniformly from 9,000 pounds (4 megagrams) or less to 18,000 pounds (8 megagrams) or more. The roller shall be equipped with tires that will afford ground contact pressures to 45 pounds per square inch (310 kiloPascals) or more. The operating load and tire air pressure shall be within the range of the manufacturer's chart or tabulations showing the contact areas and contact pressures for the full range of tire inflation pressures and for the full range of loadings for the particular tires furnished. The roller under working conditions shall provide a uniform compression under all wheels. Individual tire inflation pressures shall be within + 5 psi (+ 34 kiloPascals) of each other. The pneumatic tire roller shall be drawn by a suitable crawler type tractor, a pneumatic tired tractor, a truck of adequate tractive effort or may be of the self-propelled type. The roller, when drawn or propelled by either type of equipment, shall be considered a light pneumatic tire roller unit.

C. Medium Pneumatic Tire Roller (Type A)

The medium pneumatic tire roller (Type A) shall consist of not less than 7 pneumatic tired wheels, running on axles in such manner that the rear group of tires will cover the entire gap between adjacent tires of the forward group and mounted in a rigid frame and provided with a loading platform or body suitable for ballast loading. The front axle shall be attached to the frame in such a manner that the roller may be turned within a minimum circle. The pneumatic tire roller, under working conditions, shall have an effective rolling width of approximately 84 inches (2.1 meters) and shall be so designed that, by ballast loading, the total load may be varied uniformly from 23,500 pounds (10.5 megagrams) or less to 50,000 pounds (22.5 megagrams) or more. The roller shall be equipped with tires that will afford ground contact pressures of 80 pounds per square inch (550 kiloPascals) or more. The operating load and tire air pressure shall be within the range of the manufacturer's chart. The roller under working conditions shall provide a uniform compression under all wheels. Individual tire inflation pressures shall be within + 5 psi (+ 34 kiloPascals) of each other.

The pneumatic tire roller shall be drawn by a suitable crawler type tractor, a pneumatic tired tractor, a truck of adequate tractive effort or may be of the self-propelled type. The roller, when drawn or propelled by any type of equipment, shall be considered a medium pneumatic tire roller unit. The power unit shall have adequate tractive effort to properly move the operating roller at variable uniform speeds up to approximately 5 miles per hour (8 kilometers per hour).

D. Medium Pneumatic Tire Roller (Type B)

The medium pneumatic tire roller (Type B) shall conform to the requirements for Medium Pneumatic Tire Roller (Type A) as specified above, except that the roller shall be equipped with tires that will afford ground contact pressures to 90 psi (620 kiloPascals) or more.

232S.4 Construction Methods

The embankment layer or the base course shall be sprinkled in accordance with Standard Specification Item Nos. 201S, "Subgrade Preparation" and 210S, "Flexible Base". Rolling with a pneumatic tire roller shall start longitudinally at the sides of the designated area and shall proceed towards the center, overlapping on successive trips by at least 1/2 of the width of the pneumatic tire roller. On superelevated curves, rolling shall begin at the low sides and progress toward the high sides. Alternate trips of the roller shall be slightly different in length.

The light pneumatic tire roller shall be operated at speeds, which shall be between 3 and 11 miles per hour (between 6 and 19 kilometers per hour) for asphalt surfacing work and between 2 and 6 miles per hour (between 3 and 10 kilometers per hour) for all other work.

The medium pneumatic tire roller shall be operated at speeds as directed by the Engineer or designated representative, which produce a satisfactory product.

Sufficient rollers shall be provided to compact the material in a satisfactory manner. When operations are so isolated from one another that 1 roller unit cannot produce the required compaction satisfactorily, additional roller units shall be provided.

232S.5 Measurement and Payment

Compensation will not be allowed for materials, equipment or labor required by this item. These items shall be included in the unit price bid for the item of construction in which this item is used.

End

SPECIFIC CROSS REFERENCE MATERIALS
Specification 232S, "Rolling (Pneumatic Tire)"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 201S	Subgrade Preparation
Item No. 210S	Flexible Base

RELATED CROSS REFERENCE MATERIALS

City of Austin Contract Documents

<u>Designation</u>	<u>Description</u>
Section 00700	General Conditions

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 101S	Preparing Right of Way
Item No. 102S	Clearing and Grubbing
Item No. 110S	Street Excavation
Item No. 111S	Excavation
Item No. 130S	Borrow
Item No. 132S	Embankment
Item No. 202S	Hydrated Lime and Lime Slurry
Item No. 203S	Lime Treatment for Materials in Place
Item No. 230S	Rolling (Flat Wheel)

RELATED CROSS REFERENCE MATERIALS-Continued

Specification 232S, "Rolling (Pneumatic Tire)"

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 236S	Proof Rolling
Item No. 301S	Asphalts, Oils and Emulsions
Item No. 306S	Prime Coat
Item No. 307S	Tack Coat
Item No. 310S	Emulsified Asphalt Treatment
Item No. 320S	Two Course Surface Treatment
Item No. 340S	Hot Mix Asphaltic Concrete Pavement
Item No. 402S	Controlled Low Strength Material
Item No. 403S	Concrete for Structures

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 1000S-10	Local Street Sections
No. 1000S-11(1)	Residential and City of Austin Neighborhood Collector Street Sections
No. 1000S-11(2)	Industrial and Commercial Collector Street Sections
No. 1000S-12(1)	Primary Collector Street Sections
No. 1000S-12(2)	Primary Arterial Street Sections
No. 1000S-13(1)	Minor Arterial Street Sections (4 Lanes)
No. 1000S-13(2)	Minor Arterial Street Sections- (4 Lanes divided)
No. 1000S-14	Major Arterial Street Sections

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Item No. 100	Preparing Right of Way
Item No. 110	Excavation
Item No. 112	Subgrade Widening
Item No. 132	Embankment
Item No. 150	Blading
Item No. 158	Specialized Excavation Work
Item No. 204	Sprinkling
Item No. 210	Rolling (Flat Wheel)
Item No. 211	Rolling (Tamping)
Item No. 213	Rolling (Pneumatic Tire)
Item No. 264	Lime and Lime Slurry
Item No. 300	Asphalts, Oils and Emulsions
Item No. 301	Asphalt Anti-stripping Agents
Item No. 310	Prime Coat (Cutback Asphaltic Materials)
Item No. 314	Emulsified Asphalt Treatment
Item No. 316	Surface Treatments
Item No. 345	Asphalt Stabilized Base (Plant Mixed)

Texas Department of Transportation: Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-101-E	Surveying and Sampling Soils for Highways
Tex-103-E	Determination of Moisture Content of Soil Materials
Tex-104-E	Determination of Liquid Limit of Soils
Tex-105-E	Determination of Plastic limit of Soils
Tex-106-E	Method of Calculating the Plasticity Index of Soils

RELATED CROSS REFERENCE MATERIALS-Continued

Specification 232S, "Rolling (Pneumatic Tire)"

Texas Department of Transportation: Manual of Testing Procedures

<u>Designation</u>	<u>Description</u>
Tex-114-E	Laboratory Compaction Characteristics & Moisture Density Relationship of Subgrade & Embankment Soil
Tex-115-E	Field Method for Determination of In-Place Density of Soil & Base Materials
Tex-117-E	Triaxial Compression Tests for Disturbed Soils and Base Materials
Tex-120-E	Soil Cement Testing
Tex-121-E	Soil Lime Testing
Tex-126-E	Molding, Testing and Evaluation of Bituminous Black Base Materials
Tex-207-F	Determination of Density of Compacted Bituminous Mixtures
Tex-210-F	Determination of Asphalt Content of Bituminous Mixtures by Extraction
Tex-228-F	Determination of Asphalt Content of Bituminous Mixtures By The Nuclear Method
Tex-600-J	Sampling and Testing of Hydrated Lime, Quicklime & Commercial Lime Slurry